

Technical Information

TRU BOND 300

Multipurpose Cementitious tile adhesive for floor and Walls

Overview

A Multipurpose highly polymer modified adhesive for fixing large format stones on interior and exterior floor & walls on a variety of substrates.

Key Features

- Single component, just add water
- Offers High strength for your premium stones
- Bonds to various substrates
- ♦ Exceeds IS 15477:2019 Type 3 TS1 Adhesive standards.
- ◆ Complies with EN / ISO with a C2TES1 classification.
- Water and shock resistant
- Recommended for the wet areas like swimming pools, water bodies and washrooms.
- ◆ Can be used for tile-on-tile applications
- Can be used as slurry bond adhesive in wet-on-wet applications

Standards

- ◆TRUBOND 300 exceeds the performance requirements of IS 15477: 2019 Type 3TS1;
- ♦ Complies with EN 12004: 2017 and ISO 13007: 2010 with Class "C2" and "T" Characteristics

Areas of Application

- ♦ For Interior and Exterior Walls and Floors
- ♦ Can be used for a variety of tiles and stones
- ◆ Suitable for Substrates like, Concrete & Concrete Masonry MIVON Concrete, Tremix concrete, Vacuum Dewatered Flooring, Cement Plaster, Ceramic tile, Vitrified Tile and Natural Stone, Glass mosaic tile, Brick Masonry, Cement Terrazzo etc.

Installation

Preparation

- ♦ All Substrates should be structurally sound, clean, and free from any kinds of debonding agents, dust, grease, oils, paint, release agents, etc.
- ♦ Clean the area and completely remove all the construction debris before the application.
- ♦ All tile and non-porous surfaces should be cleaned well with neutral water-based cleaner followed by cleaning with water.

Mixing

- ♦ Use clean, potable water for mixing
- ♦ Add TruBond 300 to the clean water into the mixing pot.
- ♦ Use approximately 5.5 to 6 L of water for 20 kg of Powder.
- ♦ Use a slow speed mixer for mixing or mix it by hand.

Application

- ♦ Always, Use an appropriate Standard notched trowel for application.
- ♦ Spread the tile adhesive not more than 1 sq. m. at a time, comb it to the required depth using a suitable notched trowel.
- ♦ Place the tile/stone in the wet adhesive and adjust the tile by pressing the tile firmly into a position with a twisting action.
- ◆ Use a beating block or a Rubber mallet to embed the tile properly.

Protection

Protect the surface against rain for at least 24 hours.

Keep the floor away from general foot traffic for at least 24 hours after application.

Prohibit heavy foot traffic for 14 days.

Grouting

Grout installation shall be carried out after 24 hours of application.

Note: Wall joints can be grouted after 7 to 8 hours of application and floor joints after 24 hours of application.



Technical Information

Bulk density (kg/m³)	Technical Data (typical values)			
Dry Solid Content				
Application 100 Parts of TruBond 300 with 27 to 30 parts of water (by weight)	Bulk density (kg/m³)	1350		
Mixing ratio	Dry Solid Content	100		
Density of the mix (kg/m³) 1100	Application			
Density of the mix (kg/m³)	Mixing ratio	100 Parts of TruBond 300 with 27 to 30 parts of water (by		
PH of the mix				
Pot life				
Application Temperature 5 to 40 °C Open time 30 minutes Adjustability time 30 minutes Time to Heavy traffic 24 hours Ready for grouting 24 hours Performance (TruBond 300 mixed with water) 24 hours Parameters Requirement Typical Values Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.45 N/mm² A (Clause 5.1) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² S 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.15 N/mm² IS 15477: 2019 Heat Ageing Condition Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) So 0.50 mm ≤ 0.35 mm Sip Resistance So 0.50 mm ≤ 0.35 mm ≤ 0.35 mm				
Open time 30 minutes Adjustability time 30 minutes Time to Heavy traffic 24 hours Ready for grouting 24 hours Performance (TruBond 300 mixed with water) 22 hours Performance (TruBond 300 mixed with water) Requirement Parameters Requirement Typical Values Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.45 N/mm² Annex A (Clause 5.1) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Heat Ageing Condition Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) <t< td=""><td></td><td colspan="2">4 hours</td></t<>		4 hours		
Adjustability time 30 minutes Time to Heavy traffic 24 hours Ready for grouting 24 hours Performance (TruBond 300 mixed with water) Parameters Requirement Typical Values Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.45 N/mm² Annex A (Clause 5.1) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² Is 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² Is 15477: 2019 Wet Condition Annex B (Clause 5.2) Shear Adhesion Strength Shear Adhesion Strength Shear Adhesion Strength Is 15477: 2019 Wet Condition Annex B (Clause 5.2) Shear Adhesion Strength S	Application Temperature	5 to 40 °C		
Time to Heavy traffic 24 hours Ready for grouting 24 hours Performance (TruBond 300 mixed with water) Tensile Adhesion Strength Typical Values Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.45 N/mm² Is 15477: 2019 Wet Condition Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.15 N/mm² Is 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² 1.45 N/mm² Is 15477: 2019 Wet Condition Annex B (Clause 5.2) Shear Adhesion Strength Shea		30 minutes		
Time to Heavy traffic 24 hours Ready for grouting 24 hours Performance (TruBond 300 mixed with water) Tensile Adhesion Strength Typical Values Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.45 N/mm² Is 15477: 2019 Wet Condition Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² Is 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.15 N/mm² Is 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² 1.45 N/mm² Is 15477: 2019 Wet Condition Annex B (Clause 5.2) Shear Adhesion Strength Shea	Adjustability time	30 minutes		
Performance (TruBond 300 mixed with water) Parameters Requirement Typical Values Tensile Adhesion Strength IS 15477: 2019 Dry Condition Annex A (Clause 5.1) Minimum 1.0 N/mm² 1.75 N/mm² Tensile Adhesion Strength IS 15477: 2019 Wet Condition Annex A (Clause 5.1) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength IS 15477: 2019 Dry Condition Annex B (Clause 5.2) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Slip Resistance IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm		24 hours		
Parameters Requirement Typical Values Tensile Adhesion Strength IS 15477: 2019 Dry Condition Annex A (Clause 5.1) Minimum 1.0 N/mm² 1.75 N/mm² Tensile Adhesion Strength IS 15477: 2019 Wet Condition Annex A (Clause 5.1) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength IS 15477: 2019 Dry Condition Annex B (Clause 5.2) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Slip Resistance IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm				
Tensile Adhesion Strength Minimum 1.0 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Annex A (Clause 5.1) Minimum 1.0 N/mm² 1.45 N/mm² Tensile Adhesion Strength IS 15477: 2019 Wet Condition Minimum 1.0 N/mm² 1.45 N/mm² Annex A (Clause 5.1) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Heat Ageing Condition Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm				
IS 15477: 2019 Dry Condition Annex A (Clause 5.1)		Requirement		
Annex A (Clause 5.1) Tensile Adhesion Strength IS 15477: 2019 Wet Condition Annex A (Clause 5.1) Shear Adhesion Strength IS 15477: 2019 Dry Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Slip Resistance IS 15477: 2019 Dry Condition Annex E (Clause 5.5) Transverse Deformation: (Clause 5.6) Minimum 1.0 N/mm² 1.45 N/mm² 1.45 N/mm² 1.45 N/mm² 2.50.50 mm		Minimum 1.0 N/mm ²	1.75 N/mm ²	
Tensile Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Heat Ageing Condition Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition 4.45 N/mm² 4.45 N/mm² Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm				
IS 15477: 2019 Wet Condition Annex A (Clause 5.1) Shear Adhesion Strength IS 15477: 2019 Dry Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Slip Resistance Slip Res				
Annex A (Clause 5.1) Minimum 1.25 N/mm² 1.75 N/mm² Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Minimum 1.0 N/mm² 1.45 N/mm² Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 2.5 mm for S1 > 3 mm		Minimum 1.0 N/mm ²	1.45 N/mm ²	
Shear Adhesion Strength Minimum 1.25 N/mm² 1.75 N/mm² IS 15477: 2019 Dry Condition Minimum 1.25 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.15 N/mm² IS 15477: 2019 Heat Ageing Condition Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm				
IS 15477: 2019 Dry Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Slip Resistance S 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm S 15477: 2019 Dry Condition Annex E (Clause 5.5) ≥ 2.5 mm for S1 > 3 mm				
Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.15 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Minimum 1.0 N/mm² 1.45 N/mm² Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 2.5 mm for S1 > 3 mm		Minimum 1.25 N/mm ²	1.75 N/mm ²	
Shear Adhesion Strength Minimum 1.0 N/mm² 1.15 N/mm² IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 2.5 mm for S1 > 3 mm				
IS 15477: 2019 Heat Ageing Condition Annex B (Clause 5.2) Shear Adhesion Strength Minimum 1.0 N/mm² IS 15477: 2019 Wet Condition 1.45 N/mm² Annex B (Clause 5.2) ≤ 0.50 mm Slip Resistance ≤ 0.50 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1		10.11		
Annex B (Clause 5.2) Minimum 1.0 N/mm² 1.45 N/mm² Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≤ 0.50 mm ≤ 0.35 mm Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm		Minimum 1.0 N/mm²	1.15 N/mm²	
Shear Adhesion Strength Minimum 1.0 N/mm² 1.45 N/mm² IS 15477: 2019 Wet Condition Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) ≥ 2.5 mm for S1 > 3 mm				
IS 15477: 2019 Wet Condition Annex B (Clause 5.2) Slip Resistance IS 15477: 2019 Dry Condition Annex E (Clause 5.5) Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm	/	Minimo una 4 O NI/mana?	4 45 N/mm 2	
Annex B (Clause 5.2) ≤ 0.50 mm ≤ 0.35 mm Slip Resistance ≤ 0.50 mm ≤ 0.35 mm IS 15477: 2019 Dry Condition Annex E (Clause 5.5) < 0.50 mm		Minimum 1.0 N/mm²	1.45 N/mm²	
Slip Resistance $\leq 0.50 \text{ mm}$ $\leq 0.35 \text{ mm}$ IS 15477: 2019 Dry Condition Annex E (Clause 5.5) $\leq 0.50 \text{ mm}$ $\leq 0.35 \text{ mm}$ Transverse Deformation: (Clause 5.6) $\geq 2.5 \text{ mm}$ for S1 $> 3 \text{ mm}$				
IS 15477: 2019 Dry Condition Annex E (Clause 5.5) Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm	, ,	< 0.50 mm	< 0.35 mm	
(Clause 5.5) Z.5 mm for S1 > 3 mm		_ 0.00 IIIII	= 0.33 IIIII	
Transverse Deformation: (Clause 5.6) ≥ 2.5 mm for S1 > 3 mm				
		≥ 2.5 mm for S1	> 3 mm	
	IS 15477: 2019 Classification		1	

Coverage A 20 kg bag covers approximately 5.5 to 6.0 m² (60 to 65 ft²) using a 6 mm x 6 mm square

notched trowel for a bed of 3 mm.

Note: Coverage is approximate. For actual values, contact our marketing team.

Packaging & TruBond 300 is available as 20 and 40 kg bags.

Shelf Life Colour: Grey and White

Has a shelf life of 12 months from the date of Manufacturing when stored in a dry, elevated

area in the original unopened packaging

Warning! Keep out of reach of Children.

Product for Professional Use

Wear Suitable protective clothing, gloves while handling

For Clarifications and Usage related queries, Contact our Technical Services



Technical Information

Additional Rohith Industries **Information** Plot No 1,

Industrial Park, APIIC,

Near Sri City, Tada - 524401

Andhra Pradesh

Customer Care: +91 901416 9855

email: info@rohithindia.com

Please visit us at www.rohithindia.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. All the above information must in every case be taken as merely indicative and subject to confirmation after long time application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 08.04.2024/O